

# LAC 640 SL

## Technical sheet

Recommended use : Small structures

Characteristics	Values				Units	Standards
	Warp		Weft			
<b>General characteristics</b>						
Base cloth	1100 dTex PES HT 990 den					
Coating	PVC Lowick coating both side					
Finish	Cleangard lacquer both sides					
Weight	640				g/m <sup>2</sup>	ISO 3801
Width	250	250	300	300	cm	
Roll length	60	250	60	250	ml	

## Fabric resistance

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	28	25	daN	DIN 53.363
Adhesion	8	daN/5cm	NF EN ISO 2411	
Elongation under load	<1	<2	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance	-30	°C	NF EN 1876-2	
Warm resistance	70	°C	[24h]	
Fire resistance	M2	NF P 92 503		
	B1	DIN 4102		
	B-s2-d0	Euroclasses EN 13501-1		

SYSTEM  
LOWICK

FINITION  
CLEANGARD



REACH  
COMPLIANCE

MADE IN  
FRANCE

## SAINT CLAIR TEXTILES

415, avenue de Savoie  
F-38110

Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01

[www.saintclairtextiles.com](http://www.saintclairtextiles.com)

